

## CS 896 CONCEPTS PROFESSIONAL HYDROCHROME Interior Use

896 Concepts is a water based cellulose paint for interior application on ceilings, walls, warehouses, storage rooms, and in general where washability and stain resistance are not required. It is a very economic and satisfactory solution for professionals who wish to use it either on new surfaces or on previously painted surfaces with HYDROCHROME or cellulose based products. It dries quickly to a uniformed flat finish and it can be easily recoated. It combines great hiding power, high whiteness, easy application and good leveling properties.




### Performance Features

- Cellulose Paint of general use
- Flat even finish, hides imperfections
- High coverage & whiteness.
- Easy application and clean up, quick recoat.
- Quality economy professional coating.

**Colors:** White

**Toxicity:** Formulated without lead or mercury

**Gloss Level:** 0-5 at 60° viewing angle.



### Performance Guide:

#### Weather Resistance

No recommended for exterior use.

#### Heat Resistance

60°C.

#### Solvent Resistance

Good resistance to white spirits. Sensitive to aromatic hydro carbons and alcohols.



**VOC (Volatile Organic Compounds):** EU Limit value for this product category A/a type WB: Interior matt walls and ceilings (Gloss <25@60°), 30g/l (2010). This product contains max 4g/l VOC

#### Spreading Rate

10-12 m<sup>2</sup>/L

#### Volume Solids

65%

#### Wet Film Thickness

120 micrometres

#### Dry Film Thickness

46 micrometres

#### Dry Time at 20°C

1 hour to touch  
3-4 hours to recoat

#### Flexibility

Passes 6 mm mandrel

#### Thinning

5%-10% water

#### For Application By

Brush, Roller, Spray

### Surface Preparation

Surface to be painted must be clean, dry and free of dirt, dust, flaking paint and mildew. Dull glossy areas by sanding. Dry sanding, flame cutting and /or welding of the dry paint film will give rise to dust fumes. Wet sanding/flattening should be used wherever possible. • Ensure good ventilation during application and drying. Use suitable respiratory protective equipment. Apply two coats of CS 896 CONCEPTS PROFESSIONAL HYDROCHROME after priming the surface with CS 895 CONCEPTS PROFESSIONAL Acrylic Stabilizing Primer.

### Application

Stir thoroughly before use. Apply by brush, roller or spray. Use a short nap roller on smooth surfaces. Thin 10-20% with clean water. Do not apply at temperatures below 10° C.

### Clean Up:

Clean equipment in warm, soapy water.

### Precautions Health, Safety and Environmental Protection:

- If medical advice is needed, have product container or label at hand.
- Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.
- Keep out of reach of children
- Do not get in eyes, on skin, or on clothing
- Avoid release to the environment
- Dispose of contents and container to appropriate waste site or recycled in accordance with local and national regulation
- Keep container tightly closed.
- Contains 1,2-benzisothiazol-3(2H)-one and reaction mass of 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1).
- May produce an allergic reaction.
- Call a POISON CENTER, doctor if you feel unwell.
- Safety data sheet available on request.

TEL. POISON CENTER GR: 210 7793777

### Packaging and Storage

**Sizes:** 3 litres, 9 litres

**Flash Point:** none

**Storage:** not hazardous, no special requirements

